



TOA 4 SEASONS SATIN GLO SIEU BONG

DESCRIPTION

TOA 4 SEASONS SATIN GLO SIEU BONG is exterior emulsion paint made from Acrylic emulsion with advantages:

- + Paint film with high gloss and opacity.
- + Good resistance against severe weather condition: good light fastness, anti- color fading, chalking resistance, anti-fungus and algae, alkaline resistance and waterproofing.
- + It does not use lead, mercury, formaldehyde in the formula.

Besides, Fluorosurfactants - anti dirt pick up additives provide paint film with long lasting brightness and beauty

TYPICAL USES

TOA 4 SEASONS SATIN GLO SIEU BONG is suitable for new and previously painted exterior masonry surfaces such as concrete, mortar, cement plaster, brick, gypsum board, light cement board, etc.

PHYSICAL PROPERTIES

- **Components:** Acrylic, pigments, additives & water
- **Color:** Refer to catalogue and TCW fan-deck
- **Finish:** Hi-sheen
- **Solids by volume:** 42 ± 2
- **Theoretical coverage:** 10.5 – 14 m²/liter/coat
Actual surface coverage will be depended on the spreading of paint film ability, dry film thickness, surface irregularities, technique and wastage during painting.
- **Volatile Organic Compound (VOCs):** ≤ 70 g/L (Gloss)
- **The drying time, Relative Humidity (RH) 50%**
 - **Substrate temperature** 20°C 30°C 35°C
 - **Surface (touch) dry** 1h 0.5h 0.3h
 - **Hard dry** 6h 4h 3h
 - **Painting interval, minimum** 4h 2h 1.5h

The actual drying time and painting interval time may be longer or shorter, depending on the ambient temperature, film thickness, ventilation, humidity, number of paint coatings, etc.

RECOMMENDED PAINT SYSTEM

PAINT SYSTEM	PRODUCT	NUMBER OF COAT(s)
Putty	TOA WALL MASTIC EXTERIOR	2
Primer	TOA 4 SEASONS SEALER	1
Topcoat	TOA 4 SEASONS SATIN GLO SIEU BONG	2

Technical Data Sheet

APPLICATION INSTRUCTION

▪ SURFACE PREPARATION

New surface

Let the concrete, cement plaster and mortar must be cured at least 28 days in ambient conditions (average temperature is 25°C -30°C, relative humidity is under <75%), the surface moisture is not exceeded 16% (specialized measuring testing equipment). pH value is about 6-9.

Remove all dust, grease, wax, laitance, chalking and other contaminants from the surface by specialized machine as: grinding, sanding, vacuum cleaner, high pressure water jet and proper cleaning.

Apply 2 coats TOA WALL MASTIC EXTERIOR for smooth surface.

Old surface

Remove all dust, fungus, algae, old loose paint or other contaminants from the surface by specialized machine as: grinding, sanding, vacuum cleaner, high pressure water jet and proper cleaning.

Then, treat the areas attacked by fungus or algae with proper chemicals.

Wash the surface if required and let it fully dry, the substrate moisture must be less than 16% (specialized measuring testing equipment)

Repair the damaged area. Cracks greater than 0.1mm must be fixed and make smooth by TOA WALL MASTIC EXTERIOR

Apply 1 coat of premium multipurpose primer - TOA HYDRO QUICK PRIMER for chalky or powdery surfaces after making the surface clean.

▪ APPLICATION METHOD

Application tools: Brush, roller, conventional spray

Guiding data for airless spray

- **Nozzle tip size:** 0.021 – 0.027”
- **Spray angle degrees:** 65 – 80°
- **Pressure at nozzle:** 140 – 190 Kg/cm² (2.000-2.600 Psi)

Film thickness:

	Min	Standard	Max
- Dry film thickness:	30µm	35µm	40µm
- Wet film thickness:	71µm	83µm	95µm

Film thickness will vary and is calculated as average

Dilution:

The paint is ready to use after proper stirring until homogeneous.

If thinning is required, clean water may be added up to a maximum of 5%.

CERTIFICATES

Green Label No. 032-246-3488 - Singapore Environment Council

Conformity Regulation certified: QCVN 16:2019/BXD - National Technical Regulations on Products, Goods of Building Materials for Emulsion paint (Interior & Exterior)

Technical Data Sheet

Conformity Standard certified: TCVN 8652:2020 - National standards on wall emulsion paints – specifications

Conformity Regulation certified: QCVN 08:2020/BCT - National technical regulation on the limits of lead content in paints



STORAGE & HANDLING

Store in a dry, cool, well ventilated and shaded area. Keep out of reach of children. Storage temperature about 25°C - 35°C.

Ensure that the right primer is used. Should use putty and let it thoroughly cure before painting.

Stir well before use and once opened, entire contents should be used.

Apply when temperature is from 10°C to 35°C and relative humidity is under <75%. Surface temperature must be 3°C higher than the dew point.

HEALTH AND SAFETY

Please do not handle until all safety precautions have been read and understood.

Keep away from heat, sparks, open flames, hot surfaces. No smoking.

Wear protective gloves, respirator protection, eye protection, protective clothing.

Avoid contact with skin, eyes or ingestion. Go right to the nearest health center for help in case of ingesting paint or paint contacts with eyes.

Avoid release to the environment. Treat discarded paint according to environmental laws.

See more guidelines in the Safety Data Sheet.

PACKING SIZE

18 liter; 5 liter; 1 liter

DISCLAIMER

The information in this data sheet is given to the best of TOA's knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond TOA's control. TOA cannot guarantee anything only the quality of the product itself. TOA reserve the right to change given data without further notice.

TOA PAINT VIETNAM CO., LTD.

Factory: Lot L2,3; Road No.2, Tan Dong Hiep A IP,

Di An city, Binh Duong province

Tel: 0274 3775 678 – 3775004

Fax: 0274 3775005

Website : www.toagroup.com.vn

OFFICE

Flat 8, Room 8.5, E-Town 3 Building,

364 Cong Hoa street, ward 13, Tan Binh

Ho Chi Minh city

Tel: 028 38131999

Fax: 028 38131113

Issued date: 04/10/2024

This Technical Data Sheet supersedes those previously issued.

The Technical Data Sheet (TDS) is recommended to be read in conjunction with the Safety Data Sheet (SDS) for this product.

Page: 3/3

TOA 4 SEASONS SATIN GLO

DESCRIPTION

TOA 4 SEASONS SATIN GLO is exterior emulsion paint made from Acrylic emulsion with advantages:

- + Sheen paint film with high opacity.
- + Good resistance against severe weather condition: good light fastness, anti- color fading, chalking resistance, anti-fungus and algae, alkaline resistance and waterproofing.
- + It does not use lead, mercury, formaldehyde in the formula.

Besides, Fluorosurfactants - anti dirt pick up additives provide paint film with long lasting brightness and beauty.

TYPICAL USES

TOA 4 SEASONS SATIN GLO is suitable for new and previously painted exterior masonry surfaces such as concrete, mortar, cement plaster, brick, gypsum board, light cement board, etc.

PHYSICAL PROPERTIES

- **Components:** Acrylic, pigments, additives & water
- **Color:** Refer to catalogue and TCW fan-deck
- **Finish** Sheen
- **Solids by volume:** 40 ± 2
- **Theoretical coverage:** 10.0 -13.3 m²/liter/coat
Actual surface coverage will be depended on the spreading of paint film ability, dry film thickness, surface irregularities, technique and wastage during painting.
- **Volatile Organic Compound (VOCs):** ≤ 50 g/L
- **The drying time, Relative Humidity (RH) 50%**
 - **Substrate temperature** 20°C 30°C 35°C
 - **Surface (touch) dry** 1h 0.5h 0.3h
 - **Hard dry** 6h 4h 3h
 - **Painting interval, minimum** 4h 2h 1.5h

The actual drying time and painting interval time may be longer or shorter, depending on the ambient temperature, film thickness, ventilation, humidity, number of paint coatings, etc.

RECOMMENDED PAINT SYSTEM

PAINT SYSTEM	PRODUCT	NUMBER OF COAT(s)
Putty	TOA WALL MASTIC EXTERIOR	2
Primer	TOA 4 SEASONS SEALER	1
Topcoat	TOA 4 SEASONS SATIN GLO	2

Technical Data Sheet

APPLICATION INSTRUCTION

▪ SURFACE PREPARATION

New surface

Let the concrete, cement plaster and mortar must be cured at least 28 days in ambient conditions (average temperature is 25°C -30°C, relative humidity is under <75%), the surface moisture is not exceeded 16% (specialized measuring testing equipment). pH value is about 6-9.

Remove all dust, grease, wax, laitance, chalking and other contaminants from the surface by specialized machine as: grinding, sanding, vacuum cleaner, high pressure water jet and proper cleaning.

Apply 2 coats TOA WALL MASTIC EXTERIOR for smooth surface.

Old surface

Remove all dust, fungus, algae, old loose paint or other contaminants from the surface by specialized machine as: grinding, sanding, vacuum cleaner, high pressure water jet and proper cleaning.

Then, treat the areas attacked by fungus or algae with proper chemicals.

Wash the surface if required, and let it fully dry, the substrate moisture must be less than 16% (specialized measuring testing equipment).

Repair the damaged area. Cracks greater than 0.1mm must be fixed and make smooth by TOA WALL MASTIC EXTERIOR.

Apply 1 coat of premium multipurpose primer - TOA HYDRO QUICK PRIMER for chalky or powdery surfaces after making the surface clean.

▪ APPLICATION METHOD

Application tools: Brush, roller, conventional spray

Guiding data for airless spray

- **Nozzle tip size:** 0.021 – 0.027"
- **Spray angle degrees:** 65 – 80°
- **Pressure at nozzle:** 140 – 190 Kg/cm² (2.000-2.600 Psi)

Film thickness:

	Min	Standard	Max
- Dry film thickness:	30µm	35µm	40µm
- Wet film thickness:	75µm	88µm	100µm

Film thickness will vary and is calculated as average

Dilution:

The paint is ready to use after proper stirring until homogeneous.

If thinning is required, clean water may be added up to a maximum of 5%.

CERTIFICATES

Green Label No. 032-246-3490 - Singapore Environment Council

Conformity Regulation certified: QCVN 16:2019/BXD - National Technical Regulations on Products, Goods of Building Materials for Emulsion paint (Interior & Exterior)

Conformity Standard certified: TCVN 8652:2020 – National standards on wall emulsion paints - specifications

Technical Data Sheet

Conformity Regulation certified: QCVN 08:2020/BCT - National technical regulation on the limits of lead content in paints



STORAGE & HANDLING

Store in a dry, cool, well ventilated and shaded area. Keep out of reach of children. Storage temperature about 25°C - 35°C.

Ensure that the right primer is used. Should use putty and let it thoroughly cure before painting.

Stir well before use and once opened, entire contents should be used.

Apply when temperature is from 10°C to 35°C and relative humidity is under <75%. Surface temperature must be 3°C higher than the dew point.

HEALTH AND SAFETY

Please do not handle until all safety precautions have been read and understood.

Keep away from heat, sparks, open flames, hot surfaces. No smoking.

Wear protective gloves, respirator protection, eye protection, protective clothing.

Avoid contact with skin, eyes or ingestion. Go right to the nearest health center for help in case of ingesting paint or paint contacts with eyes.

Avoid release to the environment. Treat discarded paint according to environmental laws.

See more guidelines in the Safety Data Sheet.

PACKING SIZE

18 liter: 5 liter: 1 liter

DISCLAIMER

The information in this data sheet is given to the best of TOA's knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond TOA's control. TOA cannot guarantee anything only the quality of the product itself. TOA reserve the right to change given data without further notice.

TOA PAINT VIETNAM CO., LTD.

Factory: Lot L2,3; Road No.2, Tan Dong Hiep A IP,

Di An city, Binh Duong province

Tel: 0274 3775 678 – 3775004

Fax: 0274 3775005

Website : www.toagroup.com.vn

OFFICE

Flat 8, Room 8.5, E-Town 3 Building,

364 Cong Hoa street, ward 13, Tan Binh

Ho Chi Minh city

Tel: 028 38131999

Fax: 028 38131113